



product name		Production location	
Wapper/Rainbow Snowdust		Beek	
A mix of different kinds of clay forms the basis for this facing brick. The handform surface is covered with a white coating on a cement mix basis. The brick and the cement coating are freeze resistant, fysical characteristics in terms of air conductivity und humidity control are guaranteed.			
Colour			
Cemented white with brown and grey shades			
Format			
Moulding method		Hand form	
WF: 209 x 99 x 50 mm DF: 214 x 98 x 66 mm HF: 228 x 90 x 41 mm M50: 192 x 89 x 50 mm S-BDF: 234 x 110 x 52 mm		From one series to another, the average size may slightly differ.	
Essential Characteristics - EN771-1			
		0620-CPR-53104/07	
Dimensions: tolerance category	T2		
Dimensions: range category	R1		
Active soluble salt	S2		
Average compressive strength	>20 N/mm <sup>2</sup>	Tested to the bed face	
Normalised compressive strength	>=15 N/mm <sup>2</sup>	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	0,15 N/mm <sup>2</sup>	Value according EN998-2 Annex C	
Adhesive strength (mortar)	0,30 N/mm <sup>2</sup>	Value according EN998-2 Annex C	
Reaction to fire	A1	Category	
Water absorption	<= 12% m/md		
Water vapour permeability	50/100		
Net dry density	1850 kg/m <sup>3</sup> (D1)		
Gross dry density	1700 kg/m <sup>3</sup> (D1)		
Equivalent thermal conductivity	0,51 W/m.K	Value according EN1745, Annex A 50%	
Freeze/thaw resistance	F2		
Dangerous substances	NL-BSB	According Annex ZA.3	
Other Characteristics			
Initial rate of water absorption - Non-coated Brick	1,5 - 4.0 kg/m <sup>2</sup> .min (IW3)	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption (kg/m <sup>2</sup> .min) - Coated Brick*	NPD	Value according EN771-1:2011 - 5.3.8	
Eq. Thermal Property 10, dry mass (90/90)	NPD		
Eq. Thermal Property 10, dry mass (lambda Ui)	NPD		
Eq. Thermal Property 10, dry mass (lambda Ue)	NPD		
			
Storage & handling		Cutting	
<ul style="list-style-type: none"> <li>- Store packs on a clean surface and cover them</li> <li>- Process from multiple packs at the same time</li> <li>- Follow the Vandersanden processing guidelines</li> </ul>		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	
*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.			